

Product
Specification
Sheet



nanotechnology

Double-Walled Carbon Nanotubes DWCNT		
Measurement	Mean	Deviation
Assay % CNT % Amorphous % Ash	98% Trace < 1%	≈ 50% DWCNT ≈ 30% SWCNT ≈ 20% MWCNT ± 0.5%
Diameter	2.33 nm	1σ = 1.5 nm
Length	3 μm	1σ = 2 μm
Surface Area (BET)	450 m²/gm	
Total Metal Content	≈ 5000 ppm	

Closest to SWCNT in size, but more conducting. Ideal when you're trading size, strength and electrical conductivity.

General Inquiries info@litmusnanotechnology.com

Orders Imakepeace@litmusnanotechnology.com
(303) 659-9148

www.litmusnanotechnology.com